

# Application of Nanostructured Materials in Fabrication of Electrochemical Genosensors

Amid Rahi<sup>1</sup>, Hossein Heli<sup>1,2\*</sup>

<sup>1</sup>Department of Nanomedicine, School of Advanced Medical Sciences and Technologies, Shiraz University of Medical Sciences, Shiraz, Iran.

<sup>2</sup>Nanomedicine and Nanobiology Research Center, Shiraz University of Medical Sciences, Shiraz, Iran

Scan with your device to read the article online



\*Corresponding author:

Hossein Heli, Department of Nanomedicine, School of Advanced Medical Sciences and Technologies, Shiraz University of Medical Sciences, Shiraz, Iran.  
E-mail: heli@sums.ac.ir

Received: 09.04.2015

Revised: 15.06.2015

Accepted: 29.06.2015

**Keywords:** Genosensors, Nanostructured materials, DNA biosensor, Electrochemistry

## Abstract

A multi-walled carbon nanotube modified paste electrode (MWCN-PE) was used for determination of promethazine (PMZ) in drug formulations and blood plasma by cyclic voltammetry (CV) and differential pulse voltammetry (DPV) methods. Results revealed that the MWCN-PE shows an electrocatalytic activity toward the anodic oxidation of PMZ by a marked enhancement in the current response in buffered solution at pH 5.0. At the MWCN/CPE, the anodic peak potential of PMZ was shifted by 28.0 mV to more negative potential in comparison with bare carbon paste electrode. The detection limit for this method was 0.025  $\mu\text{mol L}^{-1}$ . Results indicated that the modified electrode could be employed for the determination of promethazine hydrochloride in pharmaceutical formulations and plasma samples.

**Abbreviations:** BHT-Butylated hydroxytoluene; TEAC-trolox-equivalent antioxidant capacity; AUC-area under the curve



<https://doi.org/10.18869/nrip.jamsat.1.1.15>

## Introduction

Electrochemical sensors/biosensors are powerful devices aimed at providing selective and sensitive determination of biologically active compounds (1-6). These devices can offer advantages such as easy miniaturization, low detection limit, wide linear response range, good stability and need to small analyte volumes.

DNA sequencing is an important area of molecular biology and clinical studies. The detection of specific gene sequences in human, viral and bacterial nucleic acids is important in some areas such as clinical diagnosis and identification of genetic mutations. In this context, electrochemical sensors/biosensors are useful.

DNA-based biosensors have attracted extensive attention in recent years. The importance of these biosensors is due to their wide range of applications, from diagnosis of many human diseases to determination of pathogenicity of diseases (7-11). Diagnosis of genetic diseases is very important in health preventive care (7, 8). Prevention and treatment of human disease requires realistic, effective and low-cost design of genomic sequence determination tools and this has many usages in gene expression monitoring, pharmacogenetic researches, drug discovery, clinical diagnosis, gene analysis, virus and bacteria determination, bioterrorism factors determination, biological wars and crime investigations (10). Genetic mutation diagnosis in the molecular level will provide reliable diagnosis of diseases before clinical signs manifestation. In addition, in relation to diagnosis of microbial pathogen agents, determination methods based on nucleic acids are more sensitive and specific than immune reaction-based methods (12). In addition, it is recommended to employ new direct and sensitive methods in bacterial diagnosis and explanation, instead of hard, harmful and time-consuming isolation and culture methods (13, 14). In order to achieve these broad goals, different methods of gene sequencing in live organisms and other complex samples were developed (9-11, 15-18). Molecular diagnosis based on gene sequence analysis have provided very sensitive and precise methods to diagnose pathogens and genetic changes. Conventional methods of analysis of certain gene sequence are based on direct sequencing or DNA hybridization.

DNA hybridization methods are simpler than direct sequencing methods. In DNA hybridization method, the target gene sequence is identified by a probe DNA that can complete the double stranded structure. This method is very efficient and specific and can recognize the target gene in a complex matrix containing different noncomplementary nucleic acids. Probe DNA is a single stranded DNA (ssDNA) containing a radioactive, light absorbing, light emitting or electrochemical active agent that can reveal the hybridization (19), because nucleic acids rarely produce distinguishable signals (9, 20). The signal transducer element will reveal the target DNA capture by the probe DNA via producing a recordable signal. One of the major research fields in DNA-based biosensors is developing these signal transducer elements. Although several DNA microarray technologies were developed, this way is going to be so dynamic by researches in order to

save costs, simplify more, make more variety, and increase sensitivity and specificity.

There usually exists a problem that the amount of DNA to be recognized is less than the detection limit of current tools (at the femtomolar (fM) or attomolar (aM) level). Therefore, the transducer signal must be amplified. In some cases, PCR method is used beside these methods (14, 21, 22).

DNA detection methods based on hybridization can be divided into two groups of homogenous and heterogeneous methods. In the homogeneous method, both probe and target are in solution phase, while in the heterogeneous method, the probe DNA is immobilized on a solid surface. In homogenous method, different optical (23-26) or electrochemical (27, 28) methods are employed to reveal the hybridization. The disadvantage of homogenous method is impossibility of continuous monitoring and making the system miniaturized. Genosensors and DNA chips based on heterogeneous methods can solve these problems. Therefore, immobilization of probe DNA is one of the important stages in the fabrication of genosensors.

### ***Immobilization of the probe DNA***

The first step in genosensor development is the immobilization of probe DNA that is the most important stage of a genosensors fabrication. General methods of probe immobilization include surface adsorption, covalent immobilization and avidin (streptavidin)-biotin interaction (29).

#### ***Surface adsorption***

This route is one of the simplest ways of probe immobilization. This method relies on electrostatic interactions between the negatively charged DNA and positive charges on a surface. For example, chitosan was employed as a cationic biopolymer for DNA immobilization (30, 31). Similarly, a mixture of polyalkylamin and polystyrene sulfonate was used in DNA immobilization (32). In addition, physical adsorption of DNA on the surface of screen-printed carbon (33), pyrolytic graphite (34), gold (35), and glassy carbon (36) were reported to fabricate electrochemical genosensors.

#### ***Covalent immobilization***

In one of covalent immobilization methods, the interaction between thiol functional group and the

gold metal is employed (37-40). A chemical reaction (covalent bond formation) between amine group of 5' end of probe DNA, and the carboxylic group via 1-ethyl-3-(3-dimethylaminopropyl) carbodiimide is also employed for probe immobilization (41-44). The probe can be immobilized on the surface of conducting polymers via this reaction (45, 46-48). Of course, the immobilization of DNA on the surface of conducting polymers is not performed only via this reaction; direct coupling between amine and carboxylic groups can be done (49-51). In this regard, polypyrrole (52-59), polyaniline, polydiaminobenzene and poly(3-4-methylenedioxythiophen) (60, 61) were used. Also, self-assemble monolayer formation was used for covalent immobilization of DNA (62). Other methods of DNA covalent immobilization include immobilization by glutaraldehyde on the surface of atomic force

microscopy (AFM) probe (63), immobilization on the surface of mercaptosilane-modified glass (64), and use of aniline derivatives (65-67).

### ***Immobilization via avidin-biotin interaction***

Avidin and streptavidin are tetrameric proteins that have four binding sites for biotin. In order to immobilize the probe DNA, avidin is attached to a surface and then biotinylated DNA is immobilized on the surface (68-72).

Some advantages and disadvantages of different immobilization methods are presented in Table 1.

**Table 1.** Advantages and disadvantage of immobilization methods.

Immobilization method	Advantages	Disadvantages
Surface adsorption	Simple, Cheap, Effective, Simple equipment and handling, Easily implement in industrial processes	Poor operation stability, Frequently reversible, Immobilization affected by different parameters (such as temperature, ionic strength and pH), The possibility of denaturation, Aggregation of biomolecules and reduces the activity, Desorption possibility
Covalent	Extraordinary stable immobilization, Better control on the immobilization procedure, Over ligand density, Better biomolecules orientation, Spatial patterning, Providing accuracy and reproducibility	Rigidity of biomolecule, Low activity recovery
Avidin-biotin binding	Strong interaction, Possibility of in-situ immobilization, Easily renewable	Relatively expensive

### ***Electrochemical genosensors***

In electrochemical genosensors, hybridization can directly be converted to an electrical signal (45, 73, 74). Therefore, the complexities and difficulties of signal conversion are reduced, and signal detection with electrochemical devices will be easily possible. Electrochemical signal transducers are more sensitive and compatible with smaller sizes. These transducers can be enzymes, ferrocene and electroreactive species interacting with DNA. Also,

some electrochemical genosensors act in the label-free fashion.

### ***Enzymatic labels***

In this route, the probe DNA or its complementary target is labeled with an enzyme. In a genosensor, a peroxidase label was used that changed o-phenylenediamine to 2,2-diaminobenzene (75). The later compound is a

chromophore and also an electroreactive species. In another study, a 26-mer sequence of ssDNA was detected using impedance spectroscopy (76). For this purpose, a thiolated oligonucleotide was immobilized on the surface of gold, and hybridization of a biotinylated target DNA provided a sandwich-like structure. Then, the obtained double strand structure reacted with a HRP-containing avidin. The resulting complex could catalyze the oxidation of 4-chloro-1-naphthol by hydrogen peroxide and resulted in an electron transfer interface. In other study, HRP-labeled liposome was used similarly (77). A nylon membrane-modified by target DNA was used in other works (78-81) and the target DNA was collected with a signal transducer on the surface of a graphite-epoxy composite. In all cases, the hybridization process was monitored by electrochemical methods through labeling with a HRP-streptavidin conjugate in the presence of hydrogen peroxide and hydroquinone. In another genosensor, cationic redox polymers containing osmium-bipyridine complex were coated on the electrode surfaces (47). The complex acted as an electron transfer mediator. After immobilization of the probe DNA, a HRP-labeled target DNA was hybridized, and the resulting complex could catalyze the reduction of hydrogen peroxide. These complexes would provide the electrical contact between peroxidase center and the electrode. This method was also used to detect the presence of a single base mismatch in an 18-mer oligonucleotide (82) so that a soy heat resistant peroxidase was used. Other copolymer of 4-methyl pyridine and

acrylamide with complexes of osmium bipyridine was also employed (83). Glucose oxidase was also used as an enzyme label. A redox cationic polymer containing osmium-bipyridine complex that can conjugate with glucose oxidase was synthesized (84). This redox polymer reacted with glucose oxidase after probe immobilization and hybridized with labeled target. In the presence of glucose, the generated current was measured. Other enzymes used to fabricate genosensors include alkaline phosphatase (30,31,85), glucose-6-phosphate dehydrogenase (32) and bilirubin oxidase (86).

## Labels interacting with DNA

### - Groove binders

One of these labels is bipyridine-ruthenium complex that oxidizes guanine through a catalytic reaction. Therefore, this label reveals the presence of guanine (33,87). Similar complexes of cobalt with bipyridine or phenanthroline can be used as labels which also bind to double stranded DNA (dsDNA) selectively and reversibly. These complexes bind to the minor groove of dsDNA. Also, complexes of cadmium with pyridine-benzamide derivatives were used to study to bind to DNA (34). Hoechst (Figure 1) is a compound that binds to the minor groove of DNA which is rich in adenine/thymine. This binds to DNA and its oxidation current is relevant to the hybridization degree (35,36). This compound was used in 32-channel array (88-90) and DNA chips (91) fabrication.




Figure 1: Chemical structure of Hoechst.

## - **DNA intercalators**

Anthracycline antibiotics like daunomycin and doxorubicin are currently used in cancer treatment. Details of daunomycin interaction with DNA were studied (92-95). This drug intercalates into the dsDNA and has more affinity to guanine/cytosine base pairs and is one of the best compounds to develop genosensors. The probe DNA can be attached to the surface of carbon electrode and its hybridization with target DNA can be followed by different electrochemical methods (96). Also, the probe can be thiolated and adsorbed at the surface of gold and hybridization can be similarly followed (97). Detection limit of this method was  $10^{-11}$  M. Doxorubicin is also a special intercalator (98, 99). This drug was also used to detect DNA with 27 base pair (100). Probe DNA immobilization with avidin-biotin interaction and hybridization detection by doxorubicin lead to electrochemical detection of mutation in neuroblastoma.

The electrochemical behavior of other intercalators, such as azo dyes, acridine, ethidium bromide, anthracyclines, tetracyclines and bis-benzamides was also studied (4-101). Anthraquinone derivatives, such as 2,6-anthraquinone disulfonic acid, were also used and electron transfer to these labels performed through a long pathway (102). Ethidium bromide, as a redox intercalator, can detect DNA at  $10^{-10}$  M level (103). Extensive studies were performed on the methylene blue-DNA interaction (104, 105, 112, 113). This compound has more affinity to intercalate to ssDNA, than dsDNA. This is due to its high affinity to bind with guanine base. Therefore, upon ssDNA hybridization, the current decreases in the voltammograms of methylene blue (106, 107). In the study of intercalation of labels to DNA, carbon nanotubes (41), glassy carbon (4) and gold (108-112) electrodes were employed. Using methylene blue, the DNA of hepatitis type B virus was detected (107). Proflavine (3,6-diaminoacridine) is also a positive-charge intercalator with no electroactivity (114). However, after hybridization and binding to DNA, the ssDNA negative is neutralized. Therefore, the hybridization can be followed using an electrochemical active species with a negative charge such as ferrocyanide ions. When ssDNA exists on an electrode surface, ferrocyanide ions show weak currents due to repulsive forces. After hybridization, proflavine intercalates into dsDNA and neutralizes its negative charge. Now

ferrocyanide ions can approach the surface and generate current proportional to hybridization degree. This method could detect DNA up to  $10^{-14}$  M (114).

## - **DNA labeling with metal nanoparticles**

In most genosensors made with metal nanoparticles, gold (115-117) and silver (118) nanoparticles were used. DNA was immobilized on a carbon surface and then hybridized with gold nanoparticles-labeled target DNA (119). This genosensor was used to detect mutation in factor V of leiden. The electrochemical signal of gold nanoparticles can be measured after their dissolution (120). These nanoparticles can be dissolved through reaction with bromine/bromhydric acid mixture and converted to gold ions. These ions were then concentrated through electrochemical reduction and their amounts were measured (121). In order to increase sensitivity, gold nanoparticles can be covered with silver after DNA hybridization. This process was performed through chemical or electrochemical reductions. After that, silver was measured (68-71,122-125) or hybridization was assessed by measuring the electrical conduction (72).

Gold nanoparticles were used to label polymeric beads. In these cases, target DNA labeled with gold nanoparticles were hybridized with the probe DNA immobilized on the surface of magnetic beads (126). After that, gold nanoparticles can be quantified.

Iron-containing nanoparticles were employed to detect DNA hybridization (127). In a method, the core/shell nanoparticles containing iron core and gold shell were used. The biotinylated target hybridized with a probe labeled with iron-gold nanoparticles on the surface of polystyrene beads covered with streptavidin. In another method, commercial magnetic beads containing iron were employed. The immobilized probe DNA hybridized with magnetic beads-labeled target DNA. Then, the iron-containing nanoparticles were dissolved and the amount of iron was measured.

In Table 2, Application of some DNA labels and their electrochemical measurement techniques are presented.

**Table 2.** Some DNA labels and their electrochemical measurement techniques. HRP: Horseradish peroxidase, DPV: Differential pulse voltammetry, IS: Impedance spectroscopy, Amp: Amperometry, CV: Cyclic voltammetry, LSV: Linear sweep voltammetry, ASV: Anodic stripping voltammetry

DNA label	Techniques	Applications	Reference
HRP	DPV	Detection of human cytomegalovirus genome	75
HRP	IS	Detection of Tay-Sachs genetic disorder	76, 77
HRP	Amp	Detection of DNA hybridization	78
HRP	IS	Detection of staphylococcus aureus genome	79
Glucose oxidase	Amp	Detection of Escherichia coli genome	84
Alkaline phosphatase	DPV	Food-contaminating pathogenic bacteria genomes	85
Glucose-6-phosphate dehydrogenase	Amp	InvA gene of Salmonella typhimurium	32
Bilirubin oxidase	DPV	Detection of DNA hybridization	86
Bipyridine-ruthenium complex	CV	Detection of the 3 Ras genes in humans (HRAS, KRAS and NRAS)	33, 87
Hoechst	LSV	Detection of v-myc oncogene	35
Daunomycine	CV	Detection of yAL3 gene	97
2,6-Anthraquinone disulfonic acid	DPV, CV	Detection of single-base mismatch	102
Ethidium bromide	CV	Detection of 24-mer deoxyribonucleic acid	103
Methylene blue	CV, DPV	Detection of hepatitis B virus genome	107
Silver nanoparticles	ASV, IS	Detection of DNA hybridization	118
Gold nanoparticles	CV, DPV	Detection of Factor V Leiden mutation	119


- ***Labeling of probe or target DNA and detection of hybridization***

The methods that use labels have some drawbacks such as plenty of noise in the background. This is due to the non-specific binding of redox labels to the electrode or DNA. In order to

overcome this problem, the redox label can be attached to a DNA sequence (signal producing DNA). Of course, the disadvantage of this method is the risk of DNA demolition or its mixing with the label. The target DNA acts as a molecular bridge between probe DNA (that is attached to the surface of an electrode), and the signal producing DNA (128-132). Therefore, two processes of

hybridization occur during the function of this type of genosensor. A schematic design of this type of genosensor is shown in Figure 2. In order to fabricate such a genosensor, a ssDNA modified electrode is made and 6-mercapto 1-hexanol molecule is immobilized between the probe strands


to prevent non-specific adsorption of probe DNA. Then, the target is hybridized with the probe and then this complex is hybridized with signal producing DNA. The label attached to the signal producing DNA can be an enzyme or a nanoparticle.



**Figure 2.** Conjugation of a redox label with target DNA.

In a research, immobilization of probe DNA was performed by an avidin bridge, and a HRP labeled-signal producing DNA was employed. The detection limit was  $10^{-13}$  M (128). In another study (130), gold nanoparticles modified with streptavidin was used as a label and then attached to a probe DNA through biotin. Then, gold nanoparticles were dissolved and their concentration was determined.

Changes in DNA structure during hybridization and double strand formation can be used to fabricate genosensors. In this case, one end of probe DNA is attached to a label and the probe goes away from electrode surface after hybridization. This process is shown in Figure 3 (131,132). Using this method, DNA at  $10^{-9}$  M in blood serum was detected (133).



**Figure 3.** Changes in DNA structure followed by hybridization and formation of double stranded structure

## Design of unlabeled genosensors Field effect genosensors

Because DNA is naturally charged, it can be used in field effect transistors. Attachment of DNA to an interface will change the potential of semi-conductive gap. This change is a result of charge variation at the interface or redistribution of charges in the inter-molecular space due to the DNA adsorption (134). Different interfaces, such as silicon nitride (135), diamond (52) and carbon nanotubes (129) were used to fabricate these genosensors.


### Electrochemical genosensor- Electrochemical inherent properties of DNA-Direct oxidation of DNA bases

Early studies on electrochemistry of DNA were based on guanine oxidation on the surface of mercury drop electrode (53), and the first method of DNA detection was its direct oxidation at the surface of mercury drop electrode (53). During the oxidation process, guanine and rarely adenine are oxidized and this is closely relevant to DNA spiral structure. Advantages of this method are simplicity and no need to any modification or manipulation of DNA (54). One of the disadvantages of this method is irreversible oxidation of DNA bases that leads to

longevity decrement of the genosensor. In most of these genosensors, oxidation current of guanine continuously increases because the total surface concentration of guanine is increased upon hybridization. Therefore, this is a major drawback of this method. To overcome this problem, inosine was replaced with guanine in the probe DNA (55, 56). Inosine forms a base pair with cytosine and any generated signal will be a result of guanine oxidation directly from hybridization (57-60). In another method, guanine oxidation process was performed via an indirect catalytic reaction through transition metal complexes (not directly at the electrode surface) (61,136,137).

### Electrochemical genosensors based on conducting polymer transduction-Impedance measurement

Electronically conducting polymers are organic polymers that have electrical properties like metals. These polymers have special electronic structures, electrical conduction, low ionizing potential and high electronegativity. The most prominent and famous of these polymers are polyaniline, poly(phenyl vinylene), polypyrrole and polythiophene (Figure 4).



**Figure 4.** The chemical structure of some conductive polymers.

These polymers can be doped by ions and have self-concentrating motivations (polarons, bipolarons and solitons) that cause their electrical conduction. Immobilization of probe DNA on the surface of polymer is performed through

entrapping, covalent binding or electrostatic/hydrophobic attractions.

For entrapment, the polymer is synthesized from its monomer in the presence of probe DNA. This also causes the probe DNA (as an anion) to be doped in the polymer. In covalent immobilization, the probe

DNA is usually functionalized by amine or acid functional groups and then attached to the polymer surface. Avidin-biotin conjugation can also be used. Since the electrical properties of conductive polymers depend on its structure, doping level and its surface interactions, electrical measurements on these polymers can produce relevant signal upon hybridization. Therefore, electrochemical impedance spectroscopy will be the most common tool in hybridization detection and genosensors response recording based on conductive polymers.

A study showed that the impedance spectra of oligonucleotide-functionalized polypyrrole had a significant difference before and after hybridization

with complementary oligonucleotide (45). Similar differences were observed in copolymer of poly(1,3-acetic acid pyrrole) and poly(3-N-hydroxyphthalimide pyrrole) (138). A genosensor based on polyaniline was presented (139) and its function is illustrated in Figure 5. To fabricate this genosensor, avidin was attached to the surface of polyaniline. Then, probe DNA that was attached to biotin at its 5' end, was immobilized at the surface of polymer. In order to obtain hybridization signal, direct oxidation of guanine and methylene blue were used. Using this genosensor, a detection concentration at 2 fM was obtained.




Figure 5. A scheme for an ultrasensitive genosensor based on polyaniline.

### ***Electrochemical genosensor based on electrochemical properties of nanostructured materials***

Unique physicochemical properties of nanostructured materials have led to widespread applications of these materials in genosensor fabrication.

#### ***Polymeric nanoparticles***

Some genosensors were fabricated from conducting polymeric nanoparticles possessing high electrical conductivity, good processability, low ionizing potential and great stability (140). The most important factors influencing electrochemical properties of these genosensors are signal transduction, thickness and shape, which are well controlled through polymer sizing. Poly (indole-6-


carboxylic acid) nanostructure was synthesized for a non-labeled genosensor with picomolar (pM) level detection-limit (141). Another genosensor was designed based on polyaniline nanostructure (142) that can detect neisseria gonorrhoea in the presence of neisseria meningitides and E.coli. An arrangement of polyaniline nanotubes provided electron transfer channels to DNA active sites and provided a detection limit of fM (143).

#### ***Metallic nanomaterials***

Metallic nanomaterials show size, surface and catalytic effects related to their small dimensions. These nanomaterials were used in genosensor fabrication as immobilizing surface for probe DNA, signal amplification or as labels. Noble metal nanoparticles such as palladium, platinum, gold and silver were more used in this area (68, 72, 130, 144). For example, platinum nanoparticles deposited on the surface of glassy carbon were

used to detect soy DNA (145). Other nanomaterials were also employed together with metal nanomaterials. For example, platinum nanoparticles and carbon nanotubes, placed in Nafion polymer, were used to fabricate genosensors and can detect  $10^{-11}$  M DNA (146). A similar study reported using palladium nanoparticles (147). Among metals, gold nanoparticles the most use in genosensors fabrication. Different strategies for using gold nanoparticles in genosensor fabrication are illustrated in Figure 6. These strategies include: a) the use of gold nanoparticles as a label, and then their dissolution and determination of the resultant gold ions, b) direct determination of the amount of gold nanoparticles, c) using silver accompanied by

conductometric detection, d) improving gold nanoparticles surface with silver, e) using gold nanoparticles as carriers of other nanoparticles, or f) other electrochemical labels.



**Figure 6.** Strategies for using gold nanoparticles in genosensor fabrication.

In a study, gold nanoparticles were labeled on DNA and employed to fabricate a genosensor with a detection limit at aM level (148). In another study, a co-polymer of 2,6 pyridine and carboxylic acid was firstly synthesized on the surface of carbon and then, a layer of gold nanoparticles was covered on the polymer (149). The probe DNA was then fixed on

the surface of gold, and methylene blue was employed as the indicator of hybridization. Catalytic effect of gold nanoparticles and biological compatibility of the polymer are both effective in performance of this genosensor. In another work, gold nanoparticles were formed at the surface of carbon electrode and then a mixture of polycystamine/polyglutamic acid was covered on it

(150). The probe DNA was immobilized on the resultant surface.

Other methods of probe DNA immobilization consisted of layer-by-layer covalent binding of gold nanoparticles and thiol-functionalized carbon nanotubes on the surface of gold electrode (151). In this genosensor, carbon nanotubes provided electron-conducting matrix, and gold nanoparticles had the role of a catalyst. A gold nanoparticles surface was covered with polyamidoamine and 3-mercaptopropionic acid for the DNA immobilization (152). Rutenium-amin complex was used as the hybridization indicator and  $10^{-14}$  M DNA concentration was detected.

### ***Metal oxide nanomaterials***

Metal oxide semiconductors have been used in designing and developing biosensors as a new class of advanced materials (153-158). Cerium oxide/chitosan nanocomposite was employed for probe DNA immobilization and further detection of colon cancer gene (159). Due to the presence of chitosan, the nanocomposite had a high biocompatibility. Methylene blue was used in this genosensor and a detection limit at  $10^{-11}$  M level was obtained. Cerium oxide was also used in fabrication of other genosensors with carbon nanotubes and the ionic liquid of (1-butyl 3-methylimidazolium hexafluoro phosphate). This genosensor was used in detecting pyruvate carboxylase gene (160). Zirconia was applied as a thin film on the surface of gold to attach a probe DNA through its end phosphate group (161). Methylene blue was the hybridization indicator. Zirconia (together with carbon nanotubes and chitosan) was the main component of another genosensor (161). Probe DNA was also immobilized on the surface of zinc oxide with a detection limit at  $10^{-11}$  M level (162). In order to immobilize zinc oxide, biopolymers (162) or sol-gel method (163) were employed. Hollow microspheres of copper (I) oxide was employed to immobilize a probe DNA to detect hepatitis B virus (164).

### ***Conclusion and outlook***

This review described the utilization of nanostructured materials for fabrication of electrochemical genosensors. The electrochemical genosensors, as powerful detection devices, have the potential to significantly impact the diagnosis of diseases, such as cancers and genetic disorders. Nanostructured materials became important components in genosensing devices since they clearly improve the performance of these

instruments. Furthermore, the application of different nanomaterials to increase the efficiency of electrochemical genosensors is a well-accepted strategy. Although many improvements are required in reproducibility and sensitivity, there is no doubt that a growing number of nanomaterial-based electrochemical genosensors will soon be offered for the diagnosis of diseases and monitoring following therapy.

### ***Acknowledgements***

We would like to thank the Research Council of Shiraz University of Medical Sciences (8741) for supporting this research.

## References

- 1- Ronkainen NJ, Halsall HB, Heineman WR. *Electrochemical biosensors*. Chem Soc Rev 2010;39(2):1747-1763.
- 2- Thevenot DR, Toth K, Durst RA, Wilson GS. *Electrochemical biosensors: recommended definitions and classification*. Biosens Bioelectron 2001;16(1-2):121-131.
- 3- Frew JE, Hill HA0. *Electrochemical biosensors*. Anal Chem 1987;59(15):933-944.
- 4- Heli H, Bathaie SZ, Mousavi MF. *Electrochemical investigation of neutral red binding to DNA at the surface*. Electrochem Commun 2004;6(11):1114-1118.
- 5- Heli H, Bathaie SZ, Mousavi MF. *An electrochemical study of neutral red-DNA interaction*. Electrochim acta 2005;51(6):1108-1116.
- 6- Heli H, Moosavi-Movahedi AA, Jabbari A, Ahmad F. *An electrochemical study of safranin O binding to DNA at the surface*. J Solid State Electrochem 2007;11(5):593-599.
- 7- Odenthal KJ, Gooding JJ. *An introduction to electrochemical DNA biosensors*. Analyst 2007;132(7):603-610.
- 8- Wenonah V, Akeson M. *Biosensors for DNA sequence detection*. Curr Opin Chem Biol 2002;6(6):816-822.
- 9- Kumar S, Kumar A. *Recent advances in DNA biosensor*. Sens Transduc J 2008;92(5):122-133.
- 10- Sassolas A, Bouvier BDL, Blum LJ. *DNA biosensors and microarrays*. Chem Rev 2008;108(13):109-131.
- 11- Orazio PD. *Biosensors in clinical chemistry*. Clin Chim Acta 2003;334(3):41-69.
- 12- Lermo A, Zacco E, Barak J, Delwiche M, Campoy S, Barbe J, et al. *Towards Q-PCR of pathogenic bacteria with improved electrochemical double-tagged genosensing detection*. Biosens Bioelectron 2008;23(12):1805-11.
- 13- Van Belkum A. *Molecular diagnostics in medical microbiology: yesterday, today and tomorrow*. Curr Opin Pharmacol 2003;3(5):497-501.
- 14- Siddiquee S, Yusof NA, Salleh AB, Abu Bakar F, Heng LY. *Electrochemical DNA biosensor for the detection of specific gene related to Trichoderma harzianum species*. Bioelectrochemistry 2010;79(1):31-6.
- 15- Dong S, Chen X. *Some new aspects in biosensors*. J Biotechnol 2002;82(4):303-23.
- 16- Wang J. *Electrochemical nucleic acid biosensors*. Anal Chim Acta 2002;469(1):63-71.
- 17- Mehrvar M, Abdi M. *Recent developments, characteristics, and potential applications of electrochemical biosensors*. Analyst Sci 2004;20(8):1113-1126.
- 18- Kerman K, Kobayashi M, Tamiya E. *Recent trends in electrochemical DNA biosensor technology*. Measur Sci Technol 2004;159(2):1-11.
- 19- Yang M, McGovern ME, Thompson M. *Genosensor technology and the detection of interfacial nucleic acid chemistry*. Analyst Chim Acta 1997;346(3):259-275.
- 20- Siddiquee S, Yusof NA, Salleh AB, Tan SG, Bakar FA, Heng LY. *DNA hybridization based on trichoderma harzianum gene probe immobilization on self-assembled monolayers on a modified gold electrode*. Sens Actuat B 2010;147(1):198-205.
- 21- Huang FC, Liao CS, Lee GB. *An integrated microfluidic chip for DNA/RNA amplification, electrophoresis separation and online optical detection*. Electrophoresis 2006;27(16):3297-3305.
- 22- Heid CA, Stevens J, Livak KJ, Williams PM. *Real time quantitative PCR*. Genome Research 1996;6(10):986-994.
- 23- Wu ZS, Jiang JH, Fu L, Shen GL, Yu RQ. *Optical detection of DNA hybridization based on fluorescence quenching of tagged oligonucleotide probes by gold nanoparticles*. Anal Biochem 2006;353(1):22-29.
- 24- Yeh HC, Ho YP, Wang TH. *Quantum dot-mediated biosensing assays for specific nucleic acid detection*. Nanomed Nanotechnol Biol Med 2005;1(2):115-121.
- 25- Cao YC, Huang ZL, Liu TC, Wang HQ, Zhu XX, Wang Z, et al. *Preparation of silica encapsulated quantum dot encoded beads for multiplex assay and its properties*. Anal Biochem 2006;351(2):193-200.
- 26- Laitala V, Ylikoski A, Raussi HM, Ollikka P, Hemmila I. *Time-resolved detection probe for homogeneous nucleic acid analyses in one-step format*. Anal Biochem 2007;361(1): 126-131.
- 27- Wang J, Liu G, Merkokui A. *Electrochemical coding technology for simultaneous detection of multiple DNA targets*. J Am Chem Soc 2003;125(11):3214-3215.
- 28- Castaneda MT, Merkokui A, Pumera M, Alegret S. *Electrochemical biosensors for biomedical applications based on gold nanoparticles*. Biosens Bioelectron 2007;22(9-10):1961-1967.
- 29- Scouten WH, Luong JHT, Brown RS. *Enzyme or protein immobilization techniques for applications in biosensor design*. Trends Biotechnol 1995;13(5):178-185.
- 30- Carpinì G, Lucarelli F, Marrazza G, Mascini M. *Oligonucleotide-modified screen-printed gold electrodes for enzyme-amplified sensing of nucleic acids*. Biosens Bioelectron 2004;20(2):167-175.
- 31- Hernandez-Santos D, Diaz-Gonzalez M, Gonzalez-Garcia MB, Costa-Garcia A. *Enzymatic genosensor on streptavidin-modified screen-printed carbon electrodes*. Anal Chem 2004;76(23):6887-6893.
- 32- Suye S, Matsuura T, Kimura T, Zheng H, Hori T, Amano Y, et al. *Amperometric DNA sensor using gold electrode modified with polymerized mediator by layer-by-layer adsorption*. Microelectron Eng 2004;81(2-4):441-447.
- 33- Drummond TG, Hill MG, Barton JK. *Electrochemical DNA sensors*. Nat Biotechnol 2003;21(6):1192-1199.
- 34- Zhang J, Song S, Wang L, Pan D, Fan C. *A gold nanoparticle-based chronocoulometric DNA sensor for amplified detection of DNA*. Nat Protoc 2007;2(11):2888-2895.
- 35- Ito K, Hashimoto K, Ishimori Y. *Quantitative analysis for solid-phase hybridization reaction and binding reaction of DNA binder to hybrids using a quartz crystal microbalance*. Anal Chim Acta 1996;327(1):29-35.
- 36- Hashimoto K, Ito K, Ishimori Y. *Sequence-specific gene detection with a gold electrode modified with DNA probes and an electrochemically active dye*. Anal Chem 1994;66(4):3830-3833.
- 37- Pavlov V, Xiao Y, Gill R, Dishon A, Kotler M, Willner I. *Amplified chemiluminescence surface detection of DNA and telomerase activity using catalytic nucleic acid labels*. Anal Chem 2004;76(13):2152-2156.
- 38- Sakao Y, Nakamura F, Ueno N, Hara M. *Hybridization of oligonucleotide by using DNA self-assembled monolayer*. Colloids Surf B: Biointerfaces 2005;40(3-4):149-152.
- 39- Legay G, Finot E, Meunier-Prest R, Cherkaoui-Malki M, Latruffe N, Dereux A. *DNA nanofilm thickness measurement on microarray in air and in liquid using an atomic force microscope*. Biosens Bioelectron 2005;21(4):627-636.
- 40- Wong ELS, Mearns FJ, Gooding JJ. *Further development of an electrochemical DNA hybridization biosensor based on long-range electron transfer*. Sens Actuat B 2005;111(4):515-521.
- 41- Wang SG, Wang RL, Sellin PJ, Zhang Q. *DNA biosensors based on self-assembled carbon nanotubes*. Biochem Biophys Res Commun 2004;325(4):1433-1437.
- 42- Teh HF, Gong HQ, Dong XD, Zeng XT, Tan ALK, Yang XH, et al. *Electrochemical biosensing of DNA with capture probe covalently immobilized onto glassy carbon surface*. Anal Chim Acta 2005;551(1-2):23-29.
- 43- Jung DH, Kim BH, Ko YK, Jung MS, Jung SK, Lee SY, Jung HT. *Covalent attachment and hybridization of DNA oligonucleotides on patterned single-walled carbon nanotube films*. Langmuir 2004;20(20):8886-8891.
- 44- Sapriğin AV, Thomas CW, Dulcey CS, Patterson CH, Spector MS. *Spectroscopic quantification of covalently immobilized oligonucleotides*. Surf Interface Anal 2004;37(1):24-32.
- 45- Peng H, Soeller C, Vigar N, Kilmartin PA, Cannell MB, Bowmaker GA, et al. *Label free electrochemical DNA sensor based on functionalised conducting copolymer*. Biosens Bioelectron 2005;20(9):1821-1828.
- 46- Lee TY, Shim YB. *Direct DNA hybridization detection based on the oligonucleotide-functionalized conductive polymer*. Anal Chem 2001;73(22):5629-5632.
- 47- De Lumley-Woodyear T, Campbell CN, Heller A. *Direct enzyme-amplified electrical recognition of a 30-base model oligonucleotide*. J Am Chem Soc 1996;118(23):5504-5505.
- 48- Gu H, Su XD, Loh KP. *Electrochemical impedance sensing of DNA hybridization on conducting polymer film-modified diamond*. J Phys Chem B 2005;109(28):13611-13618.
- 49- Korri-Yousoufi H, Yassar A. *Electrochemical probing of DNA based on oligonucleotide-functionalized polypyrrole*. Biomacromolecules 2001;2(1):58-64.
- 50- Tlili C, Korri-Yousoufi H, Ponsonnet L, Martelet C, Jaffrezic-Renault NJ. *Electrochemical impedance probing of DNA hybridisation on oligonucleotide functionalised polypyrrole*. Talanta 2005;68(1):131-137.
- 51- Garnier F, Korri-Yousoufi H, Srivastava P, Mandrand B, Delair T. *Toward intelligent polymers: DNA sensors based on oligonucleotide-functionalized polypyrroles*. Synthetic Met 1999;100(1):89.
- 52- Song K, Zhang G, Nakamura Y, Furukawa K, Hiraki T, Yang J, et al. *Label-free DNA sensors using ultrasensitive diamond field-effect transistors in solution*. Phys Rev Lett 2004;74(27):41919.

- 53- Palecek E. Oscillographic polarography of highly polymerized deoxyribonucleic acid. *Nat* 1960;188(5):656-657.
- 54- Palecek E. From polarography of DNA to microanalysis with nucleic acid modified electrodes. *Electroanalysis* 1996;8(1):7-14.
- 55- Wang J, Rivas G, Fernandes JR, Paz JLL, Jiang M, Waymire R. Indicator-free electrochemical DNA hybridization biosensor. *Anal Chim Acta* 1998;375(3):197-203.
- 56- Wang J, Kawde AN. Pencil-based renewable biosensor for label-free electrochemical detection of DNA hybridization. *Anal Chim Acta* 2001;431(2):219-224.
- 57- Ozkan D, Erdem A, Kara P, Kerman K, Meric B, Hassmann J, et al. Allele-specific genotype detection of factor V Leiden mutation from polymerase chain reaction amplicons based on label-free electrochemical genosensor. *Anal Chem* 2002;74(23):5931-5936.
- 58- Kerman K, Morita Y, Takamura Y, Tamiya E. Label-free electrochemical detection of DNA hybridization on gold electrode. *Electrochem Commun* 2003;5(10):887-891.
- 59- Erdem A, Pividori MI, Del Valle M, Alegret SJ. Rigid carbon composites: a new transducing material for label-free electrochemical genosensing. *The Journal of Electroanal Chem* 2004;567(1):29-37.
- 60- Erdem A, Pividori MI, Lermo A, Bonanni A, Del Valle M, Alegret S. Genomagnetic assay based on label-free electrochemical detection using magneto-composite electrodes. *Sens Actuat B* 2006;114(2):591-598.
- 61- Johnston DH, Glasgow KC, Thorp HH. Electrochemical measurement of the solvent accessibility of nucleobases using electron transfer between DNA and metal complexes. *J Am Chem Soc* 1995;117(35):8933-8938.
- 62- Zhao YD, Pang DW, Hu S, Wang ZL, Cheng JK, Dai HP. DNA-modified electrodes, part 4: optimization of covalent immobilization of DNA on self-assembled monolayers. *Talanta* 1999;49(4):751-756.
- 63- Kocuum C, Ulgen SD, Cubukcu E, Piskin E. Atomic force microscopy tips (cantilevers) as molecular nucleic acid sensors. *Ultramicroscopy* 2006;106(4-5):326-333.
- 64- Rogers YH, Jiang-Baucom P, Huang ZJ, Bogdanov V, Anderson S, Boyce-Jacino MT. Immobilization of oligonucleotides onto a glass support via disulfide bonds: A method for preparation of DNA microarrays. *Anal Biochem* 1999;266(1):23-30.
- 65- Corgier BP, Marquette CA, Blum L. Direct electrochemical addressing of immunoglobulins: Immuno-chip on screen-printed microarray. *Biosens Bioelectron* 2007;22(7):1522-1526.
- 66- Corgier BP, Marquette CA, Blum LJ. Diazonium-protein adducts for graphite electrode microarrays modification: direct and addressed electrochemical immobilization. *J Am Chem Soc* 2005;127(51):18328-1832.
- 67- Corgier BP, Laurent A, Perriat P, Blum LJ, Marquette CA. A versatile Method for Direct and Covalent Immobilization of DNA and Proteins on Biochips. *Angew Chem Int Ed Engl* 2007;46(22):4108-4110.
- 68- Wang J, Polsky R, Xu DK. Silver-enhanced colloidal gold electrochemical stripping detection of DNA hybridization. *Langmuir* 2001;17(19):5739-5741.
- 69- Cai H, Shang C, Hsing IM. Sequence-specific electrochemical recognition of multiple species using nanoparticle labels. *Anal Chim Acta* 2004;523(1):61-68.
- 70- Hernandez-Santos D, Gonzalez-Garcia MB, Costa-Garcia A. Electrochemical determination of gold nanoparticles in colloidal solutions. *Electrochim Acta* 2000; 246(4):607-615.
- 71- Hernandez-Santos D, Gonzalez-Garcia MB, Costa-Garcia A. Electrocatalytic determination of colloidal gold particles using a carbon paste electrode pretreated in cyanide media. *Electroanalysis* 2000;12(18):1461-1466.
- 72- Park SJ, Taton TA, Mirkin CA. Array-based electrical detection of DNA with nanoparticle probes. *Science* 2002;295(34):1503-1506.
- 73- Katz E, Willner I. Probing biomolecular interactions at conductive and semiconductive surfaces by impedance spectroscopy: routes to impedimetric immunosensors, DNA-sensors, and enzyme biosensors. *Electroanalysis* 2003;15(11):913-947.
- 74- Wang J. Towards genelectronics: electrochemical biosensing of DNA hybridization. *Chem Europ J* 1995;5(2):1681-1685.
- 75- Azek F, Grossiord C, Joannes M, Limoges B, Brossier P. Hybridization assay at a disposable electrochemical biosensor for the attomole detection of amplified human cytomegalovirus DNA. *Anal Biochem* 2000;284(1):107-113.
- 76- Patolsky F, Katz E, Bardea A, Willner I. Enzyme-linked amplified electrochemical sensing of oligonucleotide-DNA interactions by means of the precipitation of an insoluble product and using impedance spectroscopy. *Langmuir* 1999;15(3):3703-3706.
- 77- Alfonta L, Singh AK, Willner I. Liposomes labeled with biotin and horseradish peroxidase: a probe for the enhanced amplification of antigen-antibody or oligonucleotide-DNA sensing processes by the precipitation of an insoluble product on electrodes. *Anal Chem* 2001;73(1):91-102.
- 78- Pividori MI, Merkoci A, Alegret S. Classical dot-blot format implemented as an amperometric hybridisation genosensor. *Biosens Bioelectron* 2001;16(9-12):1133-1142.
- 79- Pividori MI, Merkoci A, Alegret S. Graphite-epoxy composites as a new transducing material for electrochemical genosensing. *Biosens Bioelectron* 2003;19(5):473-484.
- 80- Pividori MI, Alegret S. Graphite-epoxy platforms for electrochemical genosensing. *Anal Lett* 2003;36(9):1669-1695.
- 81- Pividori MI, Merkoci A, Alegret S. Dot-blot amperometric genosensor for detecting a novel determinant of  $\beta$ -lactamase resistance in staphylococcus aureus. *Analyst* 2001; 126(9):1551-1557.
- 82- Caruana DJ, Heller AJ. Enzyme-amplified amperometric detection of hybridization and of a single base pair mutation in an 18-base oligonucleotide on a 7  $\mu$ m-diameter microelectrode. *J Am Chem Soc* 1999;121(4):769-774.
- 83- Zhang YC, Kim HH, Heller A. Enzyme-amplified amperometric detection of 3000 copies of DNA in a 10  $\mu$ L droplet at 0.5 fM concentration. *Anal Chem* 2003;75(6):3267-3269.
- 84- Xie H, Zhang CY, Gao ZQ. Amperometric detection of nucleic acid at femtomolar levels with a nucleic acid/electrochemical activator bilayer on gold electrode. *Anal Chem* 2004; 76(14):1611-1617.
- 85- Farabullini F, Lucarelli F, Palchetti I, Marrazza G, Mascini M. Disposable electrochemical genosensor for the simultaneous analysis of different bacterial food contaminants. *Biosens Bioelectron* 2007;22(6):1544-1549.
- 86- Zhang YC, Pothukuchy A, Shin W, Kim Y, Heller A. Detection of ~103 copies of DNA by an electrochemical enzyme-amplified sandwich assay with ambient O<sub>2</sub> as the substrate. *Anal Chem* 2004;76(4):4093-4097.
- 87- Napier ME, Loomis CR, Sistare MF, Kim J, Eckhardt AE, Thorp HH. Probing biomolecule recognition with electron transfer: electrochemical sensors for DNA hybridization. *Bioconjugate Chem* 2007;8(6):906-913.
- 88- Choi YS, Lee KS, Park DH. Gene detection using hoechst 33258 on a biochip. *Curr Appl Phys* 2004;6(4):777-780.
- 89- Choi YS, Lee KS, Park DH. Single nucleotide polymorphism (SNP) detection using microelectrode biochip array. *J Micromech Microeng* 2007;15(10):1938-1946.
- 90- Choi YS, Park DH. Electrochemical gene detection using multi electrode array DNA chip. *J Kore Phys Soc* 2003;4(6):1556-1559.
- 91- [http://www.toshiba.co.jp/about/press/2003\\_06/pr2001.htm](http://www.toshiba.co.jp/about/press/2003_06/pr2001.htm)
- 92- Chaires JB. Biophysical chemistry of the daunomycin-DNA interaction. *Biophys Chem* 1990;35(2-3):191-202.
- 93- Chaires JB. Equilibrium studies on the interaction of daunomycin with deoxypolynucleotides. *Biochem* 1983;22(18):4204-4211.
- 94- Chaires JB. Thermodynamics of the daunomycin-DNA interaction: Ionic strength dependence of the enthalpy and entropy. *Biopolymers* 1985;24(2):403-419.
- 95- Chaires JB, Dattagupta N, Crothers DM. Studies on interaction of anthracycline antibiotics and deoxyribonucleic acid: equilibrium binding studies on the interaction of daunomycin with deoxyribonucleic acid. *Biochem* 1982;21(17):3933-3940.
- 96- Wang J, Ozsoz M, Cai XH, Rivas G, Shiraishi H, Grant DH, et al. Interactions of antitumor drug daunomycin with DNA in solution and at the surface. *Bioelectrochem Bioenerg* 1998;45(1):33-40.
- 97- Sun X, He P, Liu S, Ye J, Fang Y. Immobilization of single-stranded deoxyribonucleic acid on gold electrode with self-assembled aminoethanethiol monolayer for DNA electrochemical sensor applications. *Talanta* 1998;47(2):487-495.
- 98- Zeman SM, Phillips DR, Crothers DM. Characterization of covalent adriamycin-DNA adducts. *PNAS* 1998;95(20):11561-11565.
- 99- Yang M, Yau HCM, Chan HL. Adsorption kinetics and ligand-binding properties of thiol-modified double-stranded DNA on a gold surface. *Langmuir* 1998;14(21):6121-6129.
- 100- Patolsky F, Katz E, Willner I. Amplified DNA detection by electrogenerated biochemiluminescence and by the catalyzed precipitation of an insoluble product on electrodes in the presence of the doxorubicin intercalator. *Angewandte Chemie* 2002; 41(14):3398-3402.
- 101- Hashimoto K, Ito K, Ishimiro Y. Novel DNA sensor for electrochemical gene detection. *Anal Chim Acta* 1994;286(12):219-224.

- 102- Wong ELS, Gooding JJ. Electronic detection of target nucleic acids by a 2,6-disulfonic acid anthraquinone intercalator. *Anal Chem* 2003;75(15):3845-3852.
- 103- Liu SH, Ye JN, He PG, Fang YH. Voltammetric determination of sequence-specific DNA by electroactive intercalator on graphite electrode. *Anal Chim Acta* 1996;335(3): 239-243.
- 104- Kerman K, Ozkan D, Kara P, Meric B, Gooding JJ, Ozsoz M. Voltammetric determination of DNA hybridization using methylene blue and self-assembled alkanethiol monolayer on gold electrodes. *Anal Chim Acta* 2002;462(1):39-47.
- 105- Erdem A, Kerman K, Meric B, Ozsoz M. Methylene blue as a novel electrochemical hybridization indicator. *Electroanalysis* 2001;13(3):219-223.
- 106- Teh HF, Gong HQ, Dong XD, Zeng XT, Tan ALK, Yang XH, et al. Electrochemical biosensing of DNA with capture probe covalently immobilized onto glassy carbon surface. *Anal Chim Acta* 2005;551(1-2):23-29.
- 107- Erdem A, Kerman K, Meric B, Akarca U, Ozsoz M. Novel hybridization indicator methylene blue for the electrochemical detection of short DNA sequences related to the hepatitis B virus. *Anal Chim Acta* 2000;422(2):139-149.
- 108- Kelley SO, Barton JK, Jackson NM, Hill MG. Electrochemistry of methylene blue bound to a DNA-modified electrode. *Bioconjug Chem* 1997;8(1):31-37.
- 109- Kelley SO, Boon EM, Barton JK, Jackson NM, Hill MG. Single-base mismatch detection based on charge transduction through DNA. *Nucleic Acids Res* 1999;27(24): 4830-4837.
- 110- Boon EM, Barton JK, Bhagat V, Nersissian M, Wang W, Hill MG. Reduction of ferricyanide by methylene blue at a DNA-modified rotating-disk electrode. *Langmuir* 2003;19(22):9255-9259.
- 111- Boon EM, Ceres DM, Drummond TG, Hill MG, Barton JK. Mutation detection by electrocatalysis at DNA-modified electrodes. *Nat Biotechnol* 2000;18(10):1318.
- 112- Boal AK, Barton JK. Electrochemical detection of lesions in DNA. *Bioconjug Chem* 2005;16(2):312-321.
- 113- Sattarahmady N, Tondro GH, Golchin M, Heli H. Gold nanoparticles biosensor of *Brucella* spp. genomic DNA: Visual and spectrophotometric detections. *Biochem Engin J* 2015;97(15):1.
- 114- Park N, Hahn JH. Electrochemical sensing of DNA hybridization based on duplex-specific charge compensation. *Anal Chem* 2004;76(4):900-906.
- 115- Daniel MC, Astruc D. Gold nanoparticles: assembly, supramolecular chemistry, quantum size related properties, and applications toward biology, catalysis, and nanotechnology. *Chem Rev* 2004;104(43):293-346.
- 116- Thaxton CS, Georganopoulou DG, Mirkin CA. Gold nanoparticle probes for the detection of nucleic acid targets. *Clinica Chimica Acta* 2006;363(1-2):120-126.
- 117- Castaneda MT, Alegret S, Merkocui A. Electrochemical sensing of DNA using gold nanoparticles. *Electroanalysis* 2007;19(7-8):743-753.
- 118- Wang M, Sun C, Wang L, Ji X, Bai Y, Li T, Li J. Electrochemical detection of DNA immobilized on gold colloid particles modified self-assembled monolayer electrode with silver nanoparticle label. *J Pharma Biomed Anal* 2003;33(5):1117-1125.
- 119- Ozsoz M, Erdem A, Kerman K, Ozkan D, Tugrul B, Topcuoglu N, Ekren H, Taylan M. Electrochemical genosensor based on colloidal gold nanoparticles for the detection of factor V leiden mutation using disposable pencil graphite electrodes. *Anal Chem* 2003; 75(9):2181-2187.
- 120- Wang J. Nanoparticle-based electrochemical DNA detection. *Anal Chim Acta* 2003;500(1-2):247-257.
- 121- Merkoci A, Aldavert M, Marin S, Alegret S. New materials for electrochemical sensing V: nanoparticles for DNA labeling. *TrAC Trends Anal Chem* 2005;24(4):341-349.
- 122- Csaki A, Kaplanek P, Moller R, Fritzsche W. The optical detection of individual DNA-conjugated gold nanoparticle labels after metal enhancement. *Nanotechnol* 2003;14(6): 1262-1268.
- 123- Lee TMH, Cai H, Hsing IM. Gold nanoparticle-catalyzed silver electrodeposition on an indium tin oxide electrode and its application in DNA hybridization Transduction. *Electroanalysis* 2004;16(19):1628-1631.
- 124- Moller R, Powell RD, Hainfeld JF, Fritzsche W. Enzymatic control of metal deposition as key step for a low-background electrical detection for DNA chips. *Nano Lett* 2005;5(7):1475.
- 125- Taton TA, Mirkin CA, Letsinger RL. Scanometric DNA array detection with nanoparticle probes. *Science* 2000;289(5485):1757-1760.
- 126- Kawde AN, Wang J. Amplified electrical transduction of DNA hybridization based on polymeric beads loaded with multiple gold nanoparticle tags. *Electroanalysis* 2004;16(1-2):101-107.
- 127- Wang J, Liu G, Merkoci A. Particle-based detection of DNA hybridization using electrochemical stripping measurements of an iron tracer. *Anal Chim Acta* 2003;482(2): 149-155.
- 128- Singh AK, Willner I. Liposomes labeled with biotin and horseradish peroxidase: A probe for the enhanced amplification of antigen-antibody or oligonucleotide-DNA sensing processes by the precipitation of an insoluble product on electrodes. *Anal Chem* 2001;73(1):91-102.
- 129- Allen B, Kichambare P, Star A. Carbon nanotube field effect transistor based biosensors. *Adv Mater* 2007;19(11):1439-1451.
- 130- Wang J, Xu D, Kawde AN, Polsky R. Metal nanoparticle based electrochemical stripping potentiometric detection of DNA hybridization. *Anal Chem* 2001;73(19):5576-5581.
- 131- Mearns F, Wong E, Short K, Hibbert D, Gooding JJ. DNA biosensor concepts based on a change in the DNA persistence length upon hybridization. *Electroanalysis* 2006;18(19-20):1971-1981.
- 132- Ricci F, Lai R, Plaxco K. Linear, redox modified DNA probes as electrochemical DNA sensors. *Chem Commun* 2007;36(8):3768-3770.
- 133- Xiao Y, Qu X, Plaxco K, Heeger AJ. Label-free electrochemical detection of DNA in blood serum via target-induced resolution of an electrode-bound DNA pseudoknot. *J Am Chem Soc* 2007;129(39):11896-11897.
- 134- Poghossian A, Ingebrandt S, Abouzar M, Schoning M. Label-free detection of charged macromolecules by using a field-effect-based sensor platform: Experiments and possible mechanisms of signal generation. *App Phys A* 2007;87(3):517-524.
- 135- Estrela P, Stewart A, Yan F, Migliorato P. Field effect detection of biomolecular interactions. *Electrochim Acta* 2005;50(4):4995-5000.
- 136- Ontko AC, Armistead PM, Kircus SR, Thorp HH. Electrochemical detection of single stranded DNA using polymer modified electrodes. *Inorganic Chem* 1999;38(25):1842-1846.
- 137- Thorp HH. Cutting out the middleman: DNA biosensors based on electrochemical oxidation. *Trends Biotechnol* 1998;16(2):117-121.
- 138- Tlili C, Korri-Youssoufi H, Ponsounet L, Martelet C, Jaffrezic-Renault NJ. Electrochemical impedance probing of DNA hybridisation on oligonucleotide-functionalised polypyrrole. *Talanta* 2005;68(1):131-137.
- 139- Arora K, Prabhakar N, Chand S, Malhotra BD. Ultrasensitive DNA hybridization biosensor based on polyaniline. *Biosens Bioelectron* 2007;23(5):613-620.
- 140- Peng H, Zhang L, Soeller C, Sejdic JT. Conducting polymers for electrochemical DNA sensing. *Biomaterials* 2009;30(11):2132-2148.
- 141- Nie G, Zhang Y, Guo Q, Zhang S. SnO<sub>2</sub>-ZnO hybrid nanofibers-based highly sensitive nitrogen dioxides sensor. *Sens Actuat B* 2009;139(1):592-595.
- 142- Singh R, Prasad R, Sumana G, Arora K, Sood S, Gupta RK, et al. STD sensor based on nucleic acid functionalized nanostructured polyaniline. *Biosens Bioelectron* 2009;24(7):2232-2238.
- 143- Chang H, Yuan Y, Shi N, Guan Y. Electrochemical DNA biosensor based on conducting polyaniline nanotube array. *Anal Chem* 2007;79(13):5111-5115.
- 144- Im Y, Vasquez RP, Lee C, Myung N, Penner R, Yun M. Single metal and conducting polymer nanowire sensors for chemical and DNA detections. *J Phys Conf Seri* 2006;38(4):61-64.
- 145- Zhu N, Chang Z, He P, Fang Y. Electrochemical DNA biosensors based on platinum nanoparticles combined carbon nanotubes. *Anal Chim Acta* 2005;545(1):21-26.
- 146- Wang J, Xu D, Polsky R. Magnetically-induced solid-state electrochemical detection of DNA hybridization. *J Am Chem Soc* 2002;124(16):4208-4209.
- 147- Qing WM, Yan DX, Yan L, Qian S, Chen JX. Electrodeposited Pt-nanoparticles DNA biosensor for the detection of specific deoxyribonucleic acid in genetically modified soybean. *Chin J Anal Chem* 2008;36(7):890-894.
- 148- Zhao J, Zhu X, Li T, Li G. Self-assembled multilayer of gold nanoparticles for amplified electrochemical detection of cytochrome c. *Analyst* 2008;133(9):1242-1245.
- 149- Hu K, Lan D, Li X, Zhang S. Electrochemical DNA biosensor based on nanoporous gold electrode and multifunctional encoded DNA Au bio bar codes. *Anal Chem* 2009; 80(23):9124-9130.

- 150- Yang J, Yang T, Feng Y, Jiao K. A DNA electrochemical sensor based on nanogold-modified poly-2,6-pyridinedicarboxylic acid film and detection of PAT gene fragment. *Anal Biochem* 2007;365(1):24-30.
- 151- Zhang Y, Wang J, Xu MA. Sensitive DNA biosensor fabricated with gold nanoparticles/poly (p-aminobenzoic acid)/carbon nanotubes modified electrode. *Colloids Surf B Biointerfaces* 2010;75(1):179-185.
- 152- Zhang Y, Zhang K, Ma H. Electrochemical DNA biosensor based on silver nanoparticles/poly(3-(3-pyridyl) acrylic acid)/carbon nanotubes modified electrode. *Anal Biochem* 2009;387(1):13-19.
- 153- Santos DH, Garcia MBG, Garcia AC. Metal-nanoparticles based electroanalysis. *Electroanalysis* 2002;14(18):1225-1302.
- 154- Pandey P, Datta M, Malhotra BD. Prospects of nanomaterials in biosensors. *Anal Lett* 2008;41(2):159-209.
- 155- Heli H, Yadegari H, Karimian K. Nanoflakes of cobalt oxide for highly sensitive sensing of two orally iron chelating drugs deferasirox and deferiprone. *J Exp Nanosci* 2011;6(5):488.
- 156- Sattarahmady N, Heli H, Faramarzi F. Nickel oxide nanotubes-carbon microparticles/Nafion nanocomposite for the electrooxidation and sensitive detection of metformin. *Talanta* 2010;82(4):1126.
- 157- Heli H, Majidi S, Sattarahmady N. Ultrasensitive sensing of N-acetyl-L-cysteine using an electrocatalytic transducer of nanoparticles of iron(III) oxide core-cobalt hexacyanoferrate shell. *Sens Actuat B* 2010;145(1):185.
- 158- Heli H, Jabbari A, Moosavi-Movahedi AA, Tabeshnia M. Electrooxidation and determination of mannitol and saccharose on a cobalt hydroxide nanoparticles-modified glassy carbon electrode. *Chem Anal (Warsaw)* 2009;54(4):619.
- 159- Wang J, Rincon O, Polsky R, Dominguez E. Electrochemical detection of DNA hybridization based on DNA-templated assembly of silver cluster. *Electrochem Commun* 2003;5(1):83-86.
- 160- Zhang W, Yang T, Zhuang X, Guo Z, Jiao K. An ionic liquid supported CeO<sub>2</sub> nanoshuttles-carbon nanotubes composite as a platform for impedance DNA hybridization sensing. *Biosens Bioelectron* 2009;24(8):2417-2422.
- 161- Zhu N, Zhang A, Wang Q, He P, Fang Y. Electrochemical detection of DNA hybridization using methylene blue and electro-deposited zirconia thin films on gold electrodes. *Anal Chim Acta* 2004;510(2):163-168.
- 162- Yang Y, Wang Z, Yang M, Li J, Zheng F, Shen G, Yu R. Electrical detection of deoxyribonucleic acid hybridization based on carbon-nanotubes/nano zirconium dioxide/chitosan-modified electrodes. *Anal Chim Acta* 2007;584(2):268-274.
- 163- Ansari AA, Singh R, Sumana G, Malhotra BD. Nano-structured zinc oxide film for sexually transmitted disease sensor. *Analyst* 2009;13(5):997-1002.
- 164- Zhu H, Wang J, Xu G. Fast synthesis of Cu<sub>2</sub>O hollow microspheres and their application in DNA biosensor of hepatitis B virus. *Cryst Growth Des* 2009;9(1):633-638.